

FEATURES	HATO Varnish is suitable for all kinds of exterior & interior wood application. Paint film is smooth and hi-gloss. Protects wood from UV light and highly resistant to any weather condition, prevent water penetration, fast-drying and light color to enhance the beauty of natural wood texture & grain. Suitable for wood structures such as house and boat as well as furniture. Not recommended for wood flooring and wood stair.																														
TECHNICAL INFORMATION	<table border="0"> <tr> <td>Type</td> <td>Alkyd Resin</td> </tr> <tr> <td>Color</td> <td>Clear</td> </tr> <tr> <td>Film appearance</td> <td>High Gloss</td> </tr> <tr> <td>Pack size</td> <td>¼, 1 and 5 Gallon</td> </tr> <tr> <td>Solid by volumn</td> <td>63 ± 2%</td> </tr> <tr> <td>Solid by weight</td> <td>70 ±21%</td> </tr> <tr> <td>Specific gravity</td> <td>0.93-1.00</td> </tr> <tr> <td>Flash point</td> <td>38 c°</td> </tr> <tr> <td>Wet film thickness</td> <td>70-80 Microns</td> </tr> <tr> <td>Dry film thickness</td> <td>40-50 Microns</td> </tr> <tr> <td>Theoretical coverage</td> <td>45-50 Sq.m./coat/gallon</td> </tr> <tr> <td></td> <td>Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated</td> </tr> <tr> <td>Touch dry (25-30°c)</td> <td>1-2 Hours</td> </tr> <tr> <td>Recoat dry (25-30°c)</td> <td>6-8 Hours</td> </tr> <tr> <td>Full cure (25-30°c)</td> <td>2-3 Days</td> </tr> </table>	Type	Alkyd Resin	Color	Clear	Film appearance	High Gloss	Pack size	¼, 1 and 5 Gallon	Solid by volumn	63 ± 2%	Solid by weight	70 ±21%	Specific gravity	0.93-1.00	Flash point	38 c°	Wet film thickness	70-80 Microns	Dry film thickness	40-50 Microns	Theoretical coverage	45-50 Sq.m./coat/gallon		Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated	Touch dry (25-30°c)	1-2 Hours	Recoat dry (25-30°c)	6-8 Hours	Full cure (25-30°c)	2-3 Days
Type	Alkyd Resin																														
Color	Clear																														
Film appearance	High Gloss																														
Pack size	¼, 1 and 5 Gallon																														
Solid by volumn	63 ± 2%																														
Solid by weight	70 ±21%																														
Specific gravity	0.93-1.00																														
Flash point	38 c°																														
Wet film thickness	70-80 Microns																														
Dry film thickness	40-50 Microns																														
Theoretical coverage	45-50 Sq.m./coat/gallon																														
	Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated																														
Touch dry (25-30°c)	1-2 Hours																														
Recoat dry (25-30°c)	6-8 Hours																														
Full cure (25-30°c)	2-3 Days																														
APPLICATION	<table border="0"> <tr> <td>Tools</td> <td>Brush or Spray gun</td> </tr> <tr> <td>Diluent</td> <td>Turpentine or White Spirit</td> </tr> <tr> <td>Dilution (%)</td> <td>1 Coat : Varnish 1 : Turpentine or White Spirit 1 by volumn 2 & 3 Coat : Varnish 1 : Turpentine or White Spirit 4 by volumn</td> </tr> </table>	Tools	Brush or Spray gun	Diluent	Turpentine or White Spirit	Dilution (%)	1 Coat : Varnish 1 : Turpentine or White Spirit 1 by volumn 2 & 3 Coat : Varnish 1 : Turpentine or White Spirit 4 by volumn																								
Tools	Brush or Spray gun																														
Diluent	Turpentine or White Spirit																														
Dilution (%)	1 Coat : Varnish 1 : Turpentine or White Spirit 1 by volumn 2 & 3 Coat : Varnish 1 : Turpentine or White Spirit 4 by volumn																														
APPLICATION SYSTEM	<table border="0"> <tr> <td>Surface Preparation</td> <td></td> </tr> <tr> <td> New surface</td> <td>Use sandpaper to sand the wood surface until smooth Fill all wood crack and hole by filler Sand again until the smooth surface is obtained The surfaces must be clean and free of dirt, grease, oil, wax, salt, and other contaminants</td> </tr> <tr> <td> Old surface</td> <td>Chalky surfaces or loose material must be removed by stiff brush The surfaces must be clean and free of dirt, wax, salt, old paint, and other contaminants</td> </tr> <tr> <td>Coating system</td> <td></td> </tr> <tr> <td> Primer</td> <td>-</td> </tr> <tr> <td> Topcoat</td> <td>Apply at least 3 coats of Hato Varnish</td> </tr> </table>	Surface Preparation		New surface	Use sandpaper to sand the wood surface until smooth Fill all wood crack and hole by filler Sand again until the smooth surface is obtained The surfaces must be clean and free of dirt, grease, oil, wax, salt, and other contaminants	Old surface	Chalky surfaces or loose material must be removed by stiff brush The surfaces must be clean and free of dirt, wax, salt, old paint, and other contaminants	Coating system		Primer	-	Topcoat	Apply at least 3 coats of Hato Varnish																		
Surface Preparation																															
New surface	Use sandpaper to sand the wood surface until smooth Fill all wood crack and hole by filler Sand again until the smooth surface is obtained The surfaces must be clean and free of dirt, grease, oil, wax, salt, and other contaminants																														
Old surface	Chalky surfaces or loose material must be removed by stiff brush The surfaces must be clean and free of dirt, wax, salt, old paint, and other contaminants																														
Coating system																															
Primer	-																														
Topcoat	Apply at least 3 coats of Hato Varnish																														
HANDLING AND STORAGE	Keep the containers in a dry, cool, well ventilated space and away from heat. Containers must be kept tightly closed.																														
HEALTH AND SAFETY	Use under well ventilated conditions. Avoid skin contact.																														