

Technical Data Sheet

Hato Lacquer LG-939 Hato Acrylic lacquer for Gold Paint

FEATURES	Hato Acrylic lacquer LG-939 for Gold Paint is a high quality lacquer coating that provides a smooth,
	durable, ultra-hard, gloss finish on substrate. Can resist to harsh weathering conditions. No lead and
	mercury added.
TECHNICAL INFORMATION	
Туре	Lacquer
Color	Clear
Film appearance	Gloss
Pack size	1 Gallon, ¼ Gallon
Flash point	-4
Wet film thickness	110-125 Microns
Dry film thickness	52.33-59.46 Microns
Theoretical coverage	30-35 Sq.m./coat/gallon
Touch dry (25-30°c)	30 Minutes
Recoat dry (25-30°c)	2-3 Hours
Full cure (25-30°c)	6-8 Hours
APPLICATION	
Tools	Brush or Spray gun
Diluent	TG-04 or Thinner acrylic
Dilution (%)	Brush: 10-20%, Spray gun: 150%
APPLICATION SYSTEM	
Surface Preparation	
	Surface must be clean, dry and free from oil, grease and contaminants before painting.
Coating system	Apply at least 1-2 coats of Hato Lacquer LG-939
HANDLING AND STORAGE	The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.
HEALTH AND SAFETY	Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be remove with suitable cleanser, soap and water. Eyes should be well flushed with clean water and medical attention sought immediately.

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under

conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

Last update: August 2019