

FEATURES	<p>HATO SUPER PRIMER All IN 1 Superior quality Multi-Purpose primer for interior & exterior is made from special Nano Technology suitable for fresh concrete, new concrete and old concrete surfaces. Excellent alkali resistance, anti- efflorescence, high penetration and excellent adhesion. Pigmented primer provides outstanding high-hiding properties that help get the job done faster and with fewer coats of paint.</p> <p>Environmentally friendly paints with no-added lead and mercury.</p>																										
TECHNICAL INFORMATION	<table border="0"> <tr> <td>Type</td> <td>Acrylic resin (Water-based)</td> </tr> <tr> <td>Color</td> <td>White</td> </tr> <tr> <td>Film appearance</td> <td>Sheen</td> </tr> <tr> <td>Pack size</td> <td>5, 2.5 and 1 Gallons</td> </tr> <tr> <td>Solid by volume</td> <td>25</td> </tr> <tr> <td>Solid by weight</td> <td>42-45</td> </tr> <tr> <td>Specific gravity</td> <td>1.303-1.357</td> </tr> <tr> <td>Wet film thickness</td> <td>95-110 microns</td> </tr> <tr> <td>Dry film thickness</td> <td>24-27 microns</td> </tr> <tr> <td>Theoretical coverage</td> <td>35-40 Sq.m./coat/gallon</td> </tr> </table> <p>Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated</p> <table border="0"> <tr> <td>Touch dry (25-30°C)</td> <td>30 Minutes</td> </tr> <tr> <td>Recoat dry (25-30°C)</td> <td>2 Hours</td> </tr> <tr> <td>Full cure (25-30°C)</td> <td>7 Day</td> </tr> </table>	Type	Acrylic resin (Water-based)	Color	White	Film appearance	Sheen	Pack size	5, 2.5 and 1 Gallons	Solid by volume	25	Solid by weight	42-45	Specific gravity	1.303-1.357	Wet film thickness	95-110 microns	Dry film thickness	24-27 microns	Theoretical coverage	35-40 Sq.m./coat/gallon	Touch dry (25-30°C)	30 Minutes	Recoat dry (25-30°C)	2 Hours	Full cure (25-30°C)	7 Day
Type	Acrylic resin (Water-based)																										
Color	White																										
Film appearance	Sheen																										
Pack size	5, 2.5 and 1 Gallons																										
Solid by volume	25																										
Solid by weight	42-45																										
Specific gravity	1.303-1.357																										
Wet film thickness	95-110 microns																										
Dry film thickness	24-27 microns																										
Theoretical coverage	35-40 Sq.m./coat/gallon																										
Touch dry (25-30°C)	30 Minutes																										
Recoat dry (25-30°C)	2 Hours																										
Full cure (25-30°C)	7 Day																										
APPLICATION	<table border="0"> <tr> <td>Tools</td> <td>Roller, Brush and Spray gun</td> </tr> <tr> <td>Dilution (%)</td> <td>Hato Super Primer All in one is ready to use after through stirring. If thinning is necessary, dilute with clean water</td> </tr> </table>	Tools	Roller, Brush and Spray gun	Dilution (%)	Hato Super Primer All in one is ready to use after through stirring. If thinning is necessary, dilute with clean water																						
Tools	Roller, Brush and Spray gun																										
Dilution (%)	Hato Super Primer All in one is ready to use after through stirring. If thinning is necessary, dilute with clean water																										
APPLICATION SYSTEM	<table border="0"> <tr> <td>Surface Preparation</td> <td></td> </tr> <tr> <td> New Surface</td> <td>Allow the surfaces dry at least 2 days in case of speedy work (concrete moisture not more than 70-80%) or allow adequate time for surface to dry out completely. Surface must be free from efflorescence. Brush down or scrape off any loose material and cement splashes.</td> </tr> <tr> <td> Old Surface</td> <td>Powdery and chalky surfaces must be scrubbed and cleaned with water. Fungus and Mildew growth must be clean off with hypochlorite solution and allow for drying out at least 2-3 days.</td> </tr> <tr> <td>Coating system</td> <td></td> </tr> <tr> <td> Primer</td> <td>Apply one coat of HATO Super Primer All in one (HA2038)</td> </tr> <tr> <td> Topcoat</td> <td>Apply 2 coats of Acrylic Emulsion Paint</td> </tr> </table>	Surface Preparation		New Surface	Allow the surfaces dry at least 2 days in case of speedy work (concrete moisture not more than 70-80%) or allow adequate time for surface to dry out completely. Surface must be free from efflorescence. Brush down or scrape off any loose material and cement splashes.	Old Surface	Powdery and chalky surfaces must be scrubbed and cleaned with water. Fungus and Mildew growth must be clean off with hypochlorite solution and allow for drying out at least 2-3 days.	Coating system		Primer	Apply one coat of HATO Super Primer All in one (HA2038)	Topcoat	Apply 2 coats of Acrylic Emulsion Paint														
Surface Preparation																											
New Surface	Allow the surfaces dry at least 2 days in case of speedy work (concrete moisture not more than 70-80%) or allow adequate time for surface to dry out completely. Surface must be free from efflorescence. Brush down or scrape off any loose material and cement splashes.																										
Old Surface	Powdery and chalky surfaces must be scrubbed and cleaned with water. Fungus and Mildew growth must be clean off with hypochlorite solution and allow for drying out at least 2-3 days.																										
Coating system																											
Primer	Apply one coat of HATO Super Primer All in one (HA2038)																										
Topcoat	Apply 2 coats of Acrylic Emulsion Paint																										
TIS	TIS 1123-2555 (Masonry Primer)																										
HANDLING AND STORAGE	Keep the containers in a dry, cool, well ventilated space and away from heat. Containers must be kept tightly closed.																										
HEALTH AND SAFETY	Use under well ventilated conditions. Avoid skin contact.																										