

<b>FEATURES</b>	<p>HATO SUPER QUICK PRIMER (Pigmented Primer) is made from special quality acrylic resin. Suitable for both fresh concrete and old concrete surfaces. Excellent alkali resistance, anti- efflorescence, high penetration and excellent adhesion. Pigmented primer provides outstanding high-hiding properties that help get the job done faster and with fewer coats of paint. Environmentally friendly paints with no-added lead and mercury.</p>
<b>TECHNICAL INFORMATION</b>	<p>Type Acrylic resin (Solvent-based)</p> <p>Color White</p> <p>Film appearance Matt</p> <p>Pack size 5 and 1 US Gallons</p> <p>Solid by volume <math>35 \pm 2</math></p> <p>Solid by weight <math>63 \pm 2</math></p> <p>Flash point 38</p> <p>Specific gravity 1.268-1.374</p> <p>Wet film thickness 75-100</p> <p>Dry film thickness 25-35</p> <p>Theoretical coverage 45-50 Sq.m./coat/gallon</p> <p>Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated</p> <p>Touch dry (25-30°C) 20-30 Minutes</p> <p>Recoat dry (25-30°C) 2 Hours</p> <p>Full cure (25-30°C) 1 Day</p>
<b>APPLICATION</b>	<p>Tools Roller, Brush and Spray gun</p> <p>Dilution (%) Hato Super Quick Primer is ready to use after through stirring. If thinning is necessary, dilute with Turpentine or White spirit 5-10% (roller and brush) / 100-200% (spray gun)</p>
<b>APPLICATION SYSTEM</b>	<p><b>Surface Preparation</b></p> <p>New Surface Allow the surfaces dry at least 2 days in case of speedy work or allow adequate time for surface to dry out completely. Surface must be free from efflorescence. Brush down or scrape off any loose material and cement splashes.</p> <p>Old Surface Powdery and chalky surfaces must be scrubbed and cleaned with water. Fungus and Mildew growth must be clean off with hypochlorite solution and allow for drying out at least 2-3 days.</p> <p><b>Coating system</b></p> <p>Primer Apply one coat of HATO Super Quick Primer (HA2037)</p> <p>Topcoat Can be topcoat with Acrylic Emulsion Paint and Alkyd Base Enamel Paint</p>
<b>TIS</b>	<p>-</p>
<b>HANDLING AND STORAGE</b>	<p>Keep the containers in a dry, cool, well ventilated space and away from heat. Containers must be kept tightly closed.</p>
<b>HEALTH AND SAFETY</b>	<p>Use under well ventilated conditions. Avoid skin contact.</p>