

FEATURES	HATO CONTACT PRIMER water-based is made from special quality acrylic resin suitable for old concrete especially for chalking and loose or scaling paint. Delivers strong adhesion, stain blocking, stain resistance, anti-fungus & algae and low odor. Environmentally friendly with no-added lead and mercury.
TECHNICAL INFORMATION	<p>Type Acrylic resin (Water-based)</p> <p>Color Clear</p> <p>Film appearance Matt</p> <p>Pack size 1, 2.5 and 5 US Gallons</p> <p>Solid by volume 17.26 – 17.78</p> <p>Solid by weight 18.50 – 19.06</p> <p>Specific gravity 1.017-1.048</p> <p>Wet film thickness 95-110 microns</p> <p>Dry film thickness 16.39-18.98 microns</p> <p>Theoretical coverage 35-40 Sq.m./coat/gallon</p> <p>Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated</p> <p>Touch dry (25-30°C) 20-30 Minutes</p> <p>Recoat dry (25-30°C) 3-4 Hours</p> <p>Full cure (25-30°C) 1 Day</p>
APPLICATION	<p>Tools Roller, Brush and Spray</p> <p>Diluent No need to mix with clean water</p> <p>Dilution (%) -</p>
APPLICATION SYSTEM	<p>Surface Preparation</p> <p>Old Surface Powdery and chalky surfaces must be scrubbed and cleaned with water. Fungus and Mildew growth must be clean off with hypochlorite solution and allow for drying out at least 2-3 days.</p> <p>Coating system</p> <p>Primer Apply 1-2 coat of HATO Contact Primer (HA2033)</p> <p>Topcoat Apply at least 2 coats of Hato Acrylic Emulsion Paint</p>
TIS	-
HANDLING AND STORAGE	Keep the containers in a dry, cool, well ventilated space and away from heat. Containers must be kept tightly closed.
HEALTH AND SAFETY	Use under well ventilated conditions. Avoid skin contact.