

<b>FEATURES</b>	HATO ACRYLIC (Primary colour) made with 100% pure acrylic emulsion. Good adhesion and long-lasting durability. It is suitable for the decoration and protection of all exterior & interior on Masonry, primed plaster, concrete, concrete blocks, brickwork, cement render, ceilings, gypsum, and wood surfaces. Good algae resistance, no lead, and mercury added.
<b>TECHNICAL INFORMATION</b>	
Type	100% Pure Acrylic Emulsion
Color	Wide range of colours. Please refer to Hato Acrylic Catalogue
Film appearance	Matt
Pack size	¼ and 1 Gallons
Solid by volume	33.77-34.78
Solid by weight	50.50-52.02
Specific gravity	1.348-1.388
Wet film thickness	95-110 microns
Dry film thickness	32.08-37.14 microns
Theoretical coverage	30-40 Sq.m./coat/gallon
Touch dry (25-30°C)	30 Minutes
Recoat dry (25-30°C)	2 Hours
Full cure (25-30°C)	At least 7 Days
<b>APPLICATION</b>	
Tools	Roller, Brush and Spray
Diluent	Clean Water
Dilution (%)	5-10% (roller and brush) / 10-20% (spray)
<b>APPLICATION SYSTEM</b>	
<b>Surface Preparation</b>	
New Surface	Allow the surfaces dry at least 2 days in case of speedy work or allow adequate time for surface to dry out completely. Surface must be free from efflorescence. Brush down or scrape off any loose material and cement splashes.
Old Surface	Powdery and chalky surfaces must be scrubbed and cleaned with water. Fungus and Mildew growth must be clean off with hypochlorite solution and allow for drying out at least 2-3 days.
<b>Coating system</b>	
Primer	Fresh/New concrete Surface: Apply 1-2 coats of Hato Super Primer All in one HA2038 (Water-based) Old Surface: Apply 1-2 coats of Hato Super Primer All in one HA2038 (Water-based)
Topcoat	Apply at least 2 coats of Hato Acrylic Primary Colour Paint
<b>TIS</b>	TIS 272-2549 (Emulsion Paints for General purposes)
<b>HANDLING AND STORAGE</b>	Keep the containers in a dry, cool, well ventilated space and away from heat. Containers must be kept tightly closed.
<b>HEALTH AND SAFETY</b>	Use under well ventilated conditions. Avoid skin contact.