

FEATURES	Hato Acrylic White pearl Paint (Fast-dry) is made of 100% pure acrylic resin with premium pearl pigment suitable for exterior & interior application. The special quality pearl pigment that delivers rich & beautiful long lasting white pearl colours. Excellent adhesion, durable and can resist to harsh weathering conditions. Anti-fungus and algae. No lead and mercury added. Resistance against staining and blackening for 10 years.
TECHNICAL INFORMATION	
Type	Acrylic White pearl Paint (Fast-dry)
Color	White pearl
Film appearance	Gloss
Pack size	1 Gallon, ¼ Gallon
Flash point	15
Wet film thickness	110-125 Microns
Dry film thickness	42.00-47.71 Microns
Theoretical coverage	30-35 Sq.m./coat/gallon
Touch dry (25-30°c)	30 Minutes
Recoat dry (25-30°c)	2-3 Hours
Full cure (25-30°c)	6 Hours
APPLICATION	
Tools	Brush or Spray gun (DO NOT USE ROLLER)
Diluent	TG-04 or Thinner acrylic
Dilution (%)	Brush: 10-20%, Spray gun: 150%
APPLICATION SYSTEM	
Surface Preparation	
New Surface	Allow adequate time for surface to dry out completely. Surface must be free from efflorescence. Brush down or scrape off any loose material and cement splashes.
Old Surface	Polish the surface with sandpaper to enhance better adhesion. Chalky or peeling surface must be thoroughly cleaned with water and leave completely dried. Apply 1-2 coats of Hato Contact primer.
Metal	Metal must be dry and free from dirt, grease and other contaminants. Ferrous substrate should be sanded or wire-brushed to remove mill scales and rust then clean off and dry.
Coating system	
Primer	Wood or cement masonry: Apply 1-2 coats of Hato Acrylic Primer (Water-based) (AG-11 White) Metal: Apply 1-2 coats of Hato Acrylic Primer (Solvent-based) (G-116 White)
Topcoat	Apply at least 2-3 coats (Brush or Spray gun) of Hato White pearl
HANDLING AND STORAGE	Keep the containers in a dry, cool, well ventilated space and away from heat. Containers must be kept tightly closed.
HEALTH AND SAFETY	Use under well ventilated conditions. Avoid skin contact.