

| | |
|------------------------------|--|
| FEATURES | GPM is emulsion Paint formulated with fungus and mould resistance with no lead and mercury added. It is ideal for the protection and decoration for interior masonry substrates such as plaster, concrete, brick, gypsum board. Good adhesion. Good algae resistance, no lead and mercury added. |
| TECHNICAL INFORMATION | |
| Type | Emulsion paint |
| Color | White |
| Film appearance | Matt |
| Pack size | 5 Gallons |
| Solid by volumn | 28 |
| Solid by weight | 50-51 |
| Specific gravity | 1.429-1.487 |
| Wet film thickness | 95-110 micron |
| Dry film thickness | 27-31 micron |
| Theoretical coverage | 35-40 Sq.m./coat/gallon |
| | Remark - Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated |
| Touch dry (25-30°c) | 30 Minutes |
| Recoat dry (25-30°c) | 2 Hours |
| Full cure (25-30°c) | At least 7 Days |
| APPLICATION | |
| Tools | Roller, Brush and Spray |
| Diluent | Clean Water |
| Dilution (%) | 5-10% (roller and brush) / 10-20% (spray) |
| APPLICATION SYSTEM | |
| Surface Preparation | |
| New Surface | Allow adequate time for surface to dry out completely. Surface must be free from efflorescence. Brush down or scrape off any lose material and cement splashes. |
| Old Surface | Powdery and chalky surfaces must be scrubbed and cleaned with water. Fungus and Mildew growth must be clean off with hypochlorite solution and allow for drying out at least 2-3 days. |
| Coating system | |
| Primer | New concrete Surface: Apply 1-2 coats of GPM Primer GP2060 (Water-based) Old Surface: Apply 1-2 coats of NOC Super Primer 2 in 1 NO2012 (Water-based) |
| Topcoat | Apply at least 2 coats of GPM Acrylic Emulsion Paint |
| TIS | - |
| HANDLING AND STORAGE | Keep the containers in a dry, cool, well ventilated space and away from heat. Containers must be kept tightly closed. |
| HEALTH AND SAFETY | Use under well ventilated conditions. Avoid skin contact. |